

Product Information

XIAMETER® PMX-200 Silicone Fluid, 100,000-1,000,000 cSt

Silicone fluid for foam control agent and additive applications

FEATURES

- High-viscosity, cost-effective dimethicone conditioning agent
- High compressibility and shearability without breakdown
- High flash point
- High damping action
- High oxidation resistance
- Low fire hazard
- Low reactivity and vapor pressure
- Low surface energy
- Low pour point
- Good heat stability
- Nongreasy, nonocclusive and nonstinging on skin
- Essentially inert and nontoxic
- Excellent water repellent, release, dielectric and antifoam properties
- Soluble in a wide range of solvents

BENEFITS

For industrial applications

- Effective foam control at low addition levels

For personal care applications

- Provides easy combing and detangling for wet or dry hair
- Provides lubricious, smooth feel to the hair
- Adds gloss and softness

COMPOSITION

- High-viscosity dimethicone fluid
- Linear polydimethylsiloxane polymers typically have the following typical chemical composition:
 $(\text{CH}_3)_3\text{SiO}[\text{SiO}(\text{CH}_3)_2]_n\text{Si}(\text{CH}_3)_3$

APPLICATIONS

- For foam control in petroleum production and refinery operations
- Conditioning agent for hair care products, particularly conditioning shampoos and rinse-off conditioners

DESCRIPTION

XIAMETER PMX-200 Silicone Fluid is a high-viscosity polydimethylsiloxane polymer primarily used for foam control in nonaqueous processes. In petroleum processing, it provides effective foam control at extremely small addition levels. XIAMETER PMX-200 Silicone Fluid is also suitable for use in personal care applications. The high-molecular-weight dimethicone provides easy combing and detangling for wet or dry hair, and adds softness, smoothness and gloss.

HOW TO USE

As an Antifoam

The starting level of active material recommended is 10 ppm; in many cases, the optimal usage level may be approximately 1 ppm. XIAMETER PMX-200 Silicone Fluid is typically prediluted in a hydrocarbon solvent, such as white spirits, toluene, xylene, diesel, naphtha or another low-molecular-weight petroleum fraction, and added continuously by metering pump.

The viscosity of the XIAMETER PMX-200 Silicone Fluid should be selected to suit the application, with primary selection criteria including insolubility in the foaming system, working temperature and ease of handling.

As a Conditioning Additive

For personal care applications, XIAMETER PMX-200 Silicone Fluid should be pre-emulsified to the desired particle size, incorporated into a shampoo base and post-stabilized. Alternatively, it can be directly emulsified into a hair care formulation.

HANDLING PRECAUTIONS

XIAMETER PMX-200 Silicone Fluid may cause temporary eye discomfort.

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE XIAMETER WEBSITE AT XIAMETER.COM, OR FROM YOUR XIAMETER REPRESENTATIVE OR DISTRIBUTOR, OR BY CALLING YOUR GLOBAL XIAMETER CONNECTION.

USABLE LIFE AND STORAGE

When stored at or below 40°C (104°F) in the original unopened containers, this product has a usable life of 36 months from the date of production.

TYPICAL PROPERTIES

Test	Unit	Result				
		100,000 cSt	300,000 cSt	500,000 cSt	600,000 cSt	1,000,000 cSt
Appearance		Crystal clear	Crystal clear	Crystal clear	Crystal clear	Crystal clear
Specific Gravity at 25°C (77°F)		0.977	0.977	0.977	0.978	0.978
Refractive Index at 25°C (77°F)		1.4037	1.4037	1.4037	1.4037	1.4037
Color, APHA		5	5	5	5	5
Flash Point, Open Cup	°C (°F)	>326 (>620)	>321 (>609.8)	>321 (>609.8)	>321 (>609.8)	>321 (>609.8)
Acid Number, BCP		trace	trace	trace	trace	trace
Melt Point ^{1,2}	°C (°F)	-23 (-9)	N/A	N/A	N/A	N/A
Pour Point	°C (°F)	-33 (-27)			-25 (-13)	-25 (-13)
Surface Tension at 25°C (77°F)	dynes/cm	—			21.6	21.6
Volatile Content, at 150°C (302°F)	percent	0.30	0.30	0.30	0.30	0.30
Viscosity Stability, at 25°C (77°F), after 16 hr exposure at 150°C (302°F)	percent change	-2.4				
Viscosity Temperature Coefficient		0.61	0.61	0.61	0.61	0.61
Coefficient of Expansion	cc/cc/°C	0.00096	0.00096	0.00096	0.00096	0.00096
Thermal Conductivity at 50°C (122°F)	g cal/cm•sec•°C	0.00038	0.00038	0.00038	0.00038	0.00038
Solubility Parameter ³		7.4				
Solubility in Typical Solvents						
Chlorinated Solvents		High				
Aromatic Solvents		High				
Aliphatic Solvents		High				
Dry Alcohols		Poor				
Water		Poor				

¹The melt point temperature is a typical value and may vary somewhat due to molecular distribution. If the melting point is critical to your application, then several lots should be thoroughly evaluated.

²Due to different rates of cooling, this test method may yield pour points lower than the temperature at which these fluids would melt.

³Fedors Method: R.F. Fedors, *Polymer Engineering and Science*, Feb. 1974.

N/A = Not applicable.

LIMITATIONS

This product is neither tested nor represented as suitable for medical or pharmaceutical uses. Not intended for human injection. Not intended for food use.

HEALTH AND ENVIRONMENTAL INFORMATION

To support customers in their product safety needs, Dow Corning has an extensive Product Stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each area.

For further information, please see our website, www.xiameter.com, or consult your local XIAMETER representative.

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow Corning's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.

DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.